

# Photoemission Spectroscopy

Dr. Xiaoyu Cui

May.11.2013


# Outline

---


- ❖ Introduction
- ❖ What you need to know...
- ❖ Scientific view
- ❖ Other...

# Introduction


The photoelectric effect



First experimental work performed by H.Hertz (1886),  
W.Halwachs(1998),von Lenard(1900)  
Theoretical explanation by Einstein(1905)





Fermi surface




Many properties of solids are determined by electrons near  $E_F$ ;  
(conductivity, magnetism, superconductivity)  
Only a narrow energy range around  $E_F$  is relevant for those properties

# Advantage or disadvantage

PES is really surface sensitive  
Within VUV region



Cross sections are very small at  
high photon energy region!!



# What's the interest in PES community?

---

Physicist:

Know: sample quality; physical properties (resistance; magnetic..)

Want to know: Why? How to build the connection?


Prefer to use: Angular resolved photoemission spectroscopy (ARPES)

Chemist:


Know: possible elements or compounds inside the system.


Want to know: Chemical shifts? Bonding? Procedure? Reaction?

Prefer to use: Traditional photoemission spectroscopy (XPS); Ambient pressure photoemission spectroscopy (APPES)





Courtesy of Luc Patthey (SLS)
























































# WHAT HAPPENED IN YOUR XPS LAB..


## Energy Conservation

$$E_{kin} = h\nu - \phi - |E_B|$$

You know  $h\nu$  from Lab XPS using Al; Mg sources.  
Excitation energy are fixed at **1486.6** and **1253.6** eV


You should ask for  $\phi$  (work function) from lab scientist.  
(ask them to make a Au Fermi at the same time if possible)  
\*Work function will change with different system by few hundred meV

You know how to transfer to binding energy from kinetic energy



**YOU ARE A EXPERT NOW!!!!!!!!!!**


# Quasi-particle



Many-body interactions lead to a renormalization of the non-interacting electron dispersion (changes the effective mass of electrons) and a finite lifetime


# Interaction Effects in Band Dispersion

Computer simulation of Quasi-particle dispersion  
Including many-body interactions



High-resolution ARPES with tunable synchrotron radiation  
to determine the mass enhancement  $m^*/m_b$


# Lifetime broadening mode



electron-phonon coupling

$$\Gamma_{el-ph}$$


Debye temp.  
~0.04 eV



electron-electron interaction

$$\Gamma_{el-el}$$


Band width  
3~5 eV



electron-magnon coupling

$$\Gamma_{el-mag}$$

Mag. DOS  
~0.4 eV  
for Ni, Fe



electron-impurity scattering





$$\Gamma_{el-imp}$$

energy indep.



Final state effect

# Quasiparticle evidence




# Fermi Surfaces

In condensed matter physics, the **Fermi surface** is an abstract boundary useful for predicting the thermal, electrical, magnetic, and optical properties of systems.


The shape of the Fermi surface is derived from the periodicity and symmetry of the crystalline lattice and from the occupation of electronic energy bands.

The existence of a Fermi surface is a direct consequence of the Pauli exclusion principle, which allows a maximum of one electron per quantum state.




## Fermi Surface of Ni(110)

# Fermi Surfaces



$h\nu=100\text{eV}$   
Linear\_Horizontal light




$h\nu=100\text{eV}$   
Linear\_Vertical light


Matrix elements effect!



# Charging effect



metal




Insulator



# How to fix it?

Mental mesh??



Flood gun??



Possible factor: Charge density; Sample homogeneity.




# Inverse photoemission

15 nm thick film of DiMe-PTCDI



# Auger procedure

Energy




Fixed kinetic energy




$$E_{kin} = h\nu - \phi - |E_B|$$

# Spin-polarized photoemission





Bi film on Ag(111)



Surface states with different spin

# Time-resolved photoemission



Dynamic evidence



# Ambient pressure photoemission

Journal of Synchrotron Radiation

home submit subscribe search this article

iucr




J Synchrotron Radiat. 2012 September 1; 19(Pt 5): 701–704.

PMCID: PMC3423313

Published online 2012 August 7. doi: [10.1107/S0909049512032700](https://doi.org/10.1107/S0909049512032700)

## The new ambient-pressure X-ray photoelectron spectroscopy instrument at MAX-lab

Joachim Schnadt,<sup>a,\*</sup> Jan Knudsen,<sup>a</sup> Jesper N. Andersen,<sup>a,b</sup> Hans Siegbahn,<sup>c</sup> Annette Pietzsch,<sup>b</sup> Franz Hennies,<sup>b</sup> Niclas Johansson,<sup>a</sup> Nils Mårtensson,<sup>c</sup> Gunnar Öhrwall,<sup>b</sup> Stephan Bahr,<sup>d</sup> Sven Mähl,<sup>d</sup> and Oliver Schaff<sup>d</sup>



In situ!!



96th Canadian Chemistry Conference and Exhibition

**QUÉBEC, QUEBEC**

May 26-30, 2013

Chemistry Without Borders

#### Thursday AM

SS4

2104 A

#### Recent Avances in Photoemission

Organizer(s) - T. Ellis, Y. Hu, T.-K. Sham

Chair(s) - T. Ellis, X.Y. Cui

**08:00 02000** Probing the Electronic and Magnetic Properties of Bulk Materials, Buried Layers and Interfaces with Standing-wave and Hard-X-ray

Photoemission **Fadley C.S.**

**08:40 02001** De-Excitation Spectroscopy at the Ce L3-Edge of CePt3: The Auger Electron and the Fluorescence X-Ray Channel **Sham T.K.**, Liu L, **Thiess S**, **Drube W**, **Gordon R.A.**

**09:00 02002** Quantum Material Spectroscopy Center at the Canadian Light Source **Gorovikov S.**, **Yates B.**, **Damascelli A.**, **Hallin E.**, **Reininger R.**

**09:20 02003** Site-specific Electronic Properties of Compositionally Precise Gold Nanoparticles from X-ray Spectroscopy **\*\$Zhang P.**

**10:00 Coffee Break**

**10:20 02004** In Situ Electron Spectroscopy at the 3-way Interface of Vapor/Water/Nanoparticle **\*\$Brown M.A.**

**11:00 02005** Photoemission Overview at Canadian Light Source Inc. - From UPS to HXPS **\*\$Cui X.Y.**

**11:40 02006** Ceria Nano-Cubes: Dependence of the Electronic Structure on Synthetic and Experimental Conditions **Revoy M.N.**, **\*Scott R.W.J.**, **\$Grosvenor A.P.**

**12:00 02007** Oxide Thickness on a Ga-In Eutectic Alloy (EGaln): An Angle-Resolved Photoemission Study **\*\$Sodhi R.N.S.**, **Brodersen P.**, **Mims C.A.**, **Cademartiri L.**, **Thuo M.M.**, **Nijhuis C.A.**

**12:20 End of Session**

#### Thursday PM

SS4

2104 A

#### Recent Avances in Photoemission

Organizer(s) - T. Ellis, Y. Hu, T.-K. Sham

Chair(s) - T.-K. Sham, G.M. Bancroft

**14:00 02145** Recent Advances in High Resolution XPS of Non-conductor Oxides and Silicates **\*Bancroft G.M.**, **\$Nesbitt H.W.**, **Biesinger M.**

**14:40 02146** Industrial Applications of X-ray Photoelectron Spectroscopy in GE Research and Development Laboratory **\*\$Piao H.**

**15:20 02147** Cryo-XPS Study of the Adsorption of Xanthate on Pyrite **Karpuzov D.**, **Deng M.**, **Liu Q.**, **Xu Z.**

**15:40 02148** Frontiers of Photoelectron Spectroscopy **\*\$Bergersen H.**, **Åhlund J.**, **Moberg R.**

**16:00 02149** Novel Applications in Surface Science: In Situ Sample Analysis in Extreme Environments **Schulmeyer T.**

**16:20 02150** A New Type of Detector for Dynamic XPS Measurements

**Baumann P.**, **Kroemker B.**, **Pruemper G.**, **\*Winkler K.**, **\$Feltz A.**, **Henn F.**

**16:40 End of Session**